

ARR-104 Technical Information



Product	1.62 mil Arrow Clear Easy Release Polyester Overlamine
Sales Code	ARR-104

Features and Applications

Excellent acid, chemical, oil and scuff resistance.
Provides stability, durability and UV protection.
Ultra aggressive adhesive for demanding label applications.
Silent unwind is ideal for office setting digital printers.

Physical Properties

Release Coating	Easy Release Treatment
Film	0.92 mil Clear Polyester (PET)
Adhesive	0.70 mil High Grade Clear Emulsion Acrylic
Total Construction	1.62 mil +/- 10%

Typical Technical Value

Film Elongation at Break	115 % MD	ASTM D882
Adhesion to Steel	13 oz/in 30 min conditioning 17 oz/in 24 hr conditioning	180° peel at 12 in/min 180° peel at 12 in/min ASTM D3330/D3330M-04
Unwind Adhesion	0.5 oz/in 30 min conditioning	180° peel at 12 in/min ASTM D3811/D3811M-96
Application Temperature Rating	32°F to 150°F	
Service Temperature Rating	0°F to 300°F	

Roll Tolerance

Roll Length	+/- 5%
Roll Width	+/- 0.0625 in (1/16th in)
Storage and Handling	Two years when stored at 70°F and 50% relative humidity. Rolls must be transported and stored on protected surfaces. Use caution when placing or removing roll from mandrel.
Regulatory Compliance	RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, CEPA, CONEG, California Proposition 65

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.